

# **DECORATIVE SYNTHETIC PRODUCT GROUP**

# **Tempo Luxurious Synthetic Primer**

#### PRODUCT DESCRIPTION

Matte, modified alkyd resin-based, synthetic primer with high-coverage.

#### **FEATURES**

Adheres perfectly to the application surface thanks to its modified alkyd-resin component. Saves labor with easy combing ability and high-coverage strength. Creates a smooth surface and prepares the surface for top coat application.

#### **APPLICATION SURFACES**

Used safely before top coat on any kind of interior and exterior wood, concrete, exposed concrete, plaster, concrete board, plaster board, OSB, MDF, iron-steel-sheet metal surfaces.

#### **APPLICATION**

Remove any grease, dirt, rust and bloated paint residues from the application surface. Remove and repair any loose-weak layers which are not self-supporting. Comply with defined setting periods on concrete, exposed concrete and new plastered surfaces (28 days). Sand previously painted surfaces, and apply Tempo Luxurious Synthetic Primer after removing any dust. Impregnate wooden surfaces, which are to be painted for the first time, and then prime with Tempo Luxurious Synthetic Primer in a single coat. Sand previously painted metal and wooden surfaces, and apply Tempo Luxurious Synthetic Primer in a single coat after removing any dust. Apply Tempo Luxurious Synthetic paint as the top coat after applying the primer. Apply using a brush, roller or spray gun at a temperature between +5 °C and +30 °C. Clean the tools used with thinner immediately after application. Our products should be applied on substructure surfaces that are built in line with 30.06.2007 dated General Construction Specifications No. 26568.

# **Airless Spraying:**

Pressure: 140 bar

Nozzle Angle: 50°

Nozzle Size (inch): 0.013"

Thinning: 10-15%

#### THINNING RATIO

Thin Tempo Luxurious Synthetic Primer by 5-10% for brush or roller applications, and by 10-15% for spray gun applications.



# DRYING TIME (at 20 °C, 65% RH):

Touch Dry: 1-2 hours

Hard Dry: 8-10 hours

Final Coat Application: 24 hours (drying time may increase at higher relative humidity and lower temperatures).

#### **CONSUMPTION**

13 m² area can be primed in a single coat with 1 Liter.( 8 m² area can be primed in a single coat with 1 kg.) It can be change due to surface kind, thinning ratio, weather conditions and painter. Perform a controlled sample run to estimate the precise consumption.

#### **FLASH POINT**

36 °C

# **STORAGE**

Store in its original unopened packaging at room temperature. To store the paint remaining in its packaging safely, some amount of thinner used must be added until the whole surface of the paint is completely covered or the lid of the packaging must be closed firmly and inverted 180° for 1-2 times.

# **PACKAGING**

20Kg, 18Kg, 3Kg, 1Kg, 2.5 L, 0.75 L

#### **WARNING WORD**

Hazard

# HAZARD INDICATING COMPONENTS FOR LABELING:

Solvent naphtha (petroleum), medium aliphatic

### **HAZARD PHRASE**

H226 Inflammable liquid and vapor.

H304 Fatal if inhaled or swallowed.

# **PRECAUTIONARY PHRASES**

P101 If medical advice is needed, have product container or label at hand.

P102 Keep out of reach of children.

P103 Read label before use.

P210 Keep away from heat/sparks/flame/hot surfaces. - No smoking.

www.tempoboya.com.tr



P241 Use explosion proof electrical equipment/ventilation/igniter/material.

P301+P310 IF SWALLOWED: CALL NATIONAL POISON CONSULTING CENTER AT 114/Call a doctor.

P303+P361+P353 IN CASE OF SKIN (OR HAIR) CONTACT: Remove/take off all your stained clothes. Rinse your skin with water/shower.

P405 Keep locked up.

P501 Dispose of contents/container in accordance with local, regional, national and international regulations.



Complies with TS 11651. Class 1. First Coat



Complies with the G communique.

# Pose No.

15.540.1001, 15.540.1002, 15.540.1210, 15.540.1229, 15.540.1230, 15.540.1231, 15.540.1308 **Rate No.** 

10.300.1160

This technical sheet is prepared based on laboratory data at normal conditions, consult technical personnel for details that are not provided above. Otherwise, the manufacturing company cannot be held responsible for failures that may arise due to lack of knowledge. Our company reserves the right to change this information.

This product is manufactured by Betek A.Ş. with certificate of conformity to the standards TS EN ISO 9001, TS EN ISO 14001, TS 18001, TS EN ISO 50001, TS ISO 10002, TS ISO/IEC 27001.

Rev1 2021